

Approval body for construction products
and types of construction

Bautechnisches Prüfamt

An institution established by the Federal and
Laender Governments



European Technical Assessment

ETA-17/0445
of 1 June 2017

English translation prepared by DIBt - Original version in German language

General Part

Technical Assessment Body issuing the
European Technical Assessment:

Deutsches Institut für Bautechnik

Trade name of the construction product

Fix Master Injection system Fit-Ve 200
for rebar connection

Product family
to which the construction product belongs

System for post installed
rebar connection with mortar

Manufacturer

Ferrometal Oy
Karhutie 9
FI-01900 NURMIJÄRVI
FINNLAND

Manufacturing plant

Plant 1, Finnland

This European Technical Assessment
contains

15 pages including 3 annexes which form an integral part
of this assessment

This European Technical Assessment is
issued in accordance with Regulation (EU)
No 305/2011, on the basis of

Guideline for European technical approval of "Metal
anchors for use in concrete", ETAG 001 Part 5: "Bonded
anchors", April 2013,
used as European Assessment Document (EAD)
according to Article 66 Paragraph 3 of Regulation (EU)
No 305/2011.

European Technical Assessment

ETA-17/0445

English translation prepared by DIBt

Page 2 of 15 | 1 June 2017

The European Technical Assessment is issued by the Technical Assessment Body in its official language. Translations of this European Technical Assessment in other languages shall fully correspond to the original issued document and shall be identified as such.

Communication of this European Technical Assessment, including transmission by electronic means, shall be in full. However, partial reproduction may only be made with the written consent of the issuing Technical Assessment Body. Any partial reproduction shall be identified as such.

This European Technical Assessment may be withdrawn by the issuing Technical Assessment Body, in particular pursuant to information by the Commission in accordance with Article 25(3) of Regulation (EU) No 305/2011.

Specific Part

1 Technical description of the product

The subject of this European Technical Assessment is the post-installed connection, by anchoring or overlap connection joint, of reinforcing bars (rebars) in existing structures made of normal weight concrete, using the "Fix Master Injection system Fit-Ve 200 for rebar connection" in accordance with the regulations for reinforced concrete construction.

Reinforcing bars made of steel with a diameter ϕ from 8 to 32 mm and injection mortar Fix Master FIT-Ve 200 are used for rebar connections. The reinforcing bar is placed into a drilled hole filled with injection mortar and is anchored via the bond between embedded element, injection mortar and concrete.

The product description is given in Annex A.

2 Specification of the intended use in accordance with the applicable European Assessment Document

The performances given in Section 3 are only valid if the rebar connection is used in compliance with the specifications and conditions given in Annex B.

The verifications and assessment methods on which this European Technical Assessment is based lead to the assumption of a working life of the anchor of at least 50 years. The indications given on the working life cannot be interpreted as a guarantee given by the producer, but are to be regarded only as a means for choosing the right products in relation to the expected economically reasonable working life of the works.

3 Performance of the product and references to the methods used for its assessment

3.1 Mechanical resistance and stability (BWR 1)

| Essential characteristic | Performance |
|---|---------------|
| Design values of the ultimate bond resistance | See Annex C 1 |

3.2 Safety in case of fire (BWR 2)

| Essential characteristic | Performance |
|--------------------------|---|
| Reaction to fire | Rebar connections satisfy requirements for Class A1 |
| Resistance to fire | No performance assessed |

3.3 Hygiene, health and the environment (BWR 3)

Regarding dangerous substances there may be requirements (e.g. transposed European legislation and national laws, regulations and administrative provisions) applicable to the products falling within the scope of this European Technical Assessment. In order to meet the provisions of Regulation (EU) No 305/2011, these requirements need also to be complied with, when and where they apply..

3.4 Safety in use (BWR 4)

The essential characteristics regarding Safety in use are included under the Basic Works Requirement Mechanical resistance and stability.

4 Assessment and verification of constancy of performance (AVCP) system applied, with reference to its legal base

In accordance with guideline for European technical approval ETAG 001, April 2013 used as European Assessment Document (EAD) according to Article 66 Paragraph 3 of Regulation (EU) No 305/2011 the applicable European legal act is: [96/582/EC].

The system to be applied is: 1

5 Technical details necessary for the implementation of the AVCP system, as provided for in the applicable EAD

Technical details necessary for the implementation of the AVCP system are laid down in the control plan deposited with Deutsches Institut für Bautechnik.

Issued in Berlin on 1 June 2017 by Deutsches Institut für Bautechnik

Andreas Kummerow
Head of Department

beglaubigt:
Baderschneider

Figure A1: Overlapping joint for rebar connections of slabs and beams




Figure A3: End anchoring of slabs or beams (e.g. designed as simply supported)




Figure A5: Anchoring of reinforcement to cover the line of acting tensile force




Figure A2: Overlapping joint at a foundation of a wall or column where the rebars are stressed in tension





Figure A4: Rebar connection for components stressed primarily in compression. The rebars are stressed in compression



Note to Figure A1 to A5:

In the Figures no transverse reinforcement is plotted, the transverse reinforcement shall comply with EN 1992-1-1:2004+AC:2010.

Preparing of joints according to Annex B 2

Fix Master Injection system Fit-Ve 200 for rebar connection

Product description
Installed condition and examples of use for rebars

Annex A 1

Fix Master Injection system Fit-Ve 200:


Injection mortar: Fix Master FIT-Ve 200

Typ "coaxial": 150 ml, 280 ml,
300 ml up to 333 ml and
380 ml up to 420 ml Kartusche

Type "side-by-side":
235 ml, 345 ml and 825 ml
cartridge



Imprint: Fix Master FIT-Ve 200,
processing notes, charge-code, shelf life,
hazard-code, curing- and processing time
(depending on the temperature), with as well as
without travel scale




Imprint: Fix Master FIT-Ve 200,
processing notes, charge-code, shelf life,
hazard-code, curing- and processing time
(depending on the temperature), with as well as
without travel scale

Static Mixer

CRW 14W

TAH 18W



**Piston plug and
mixer extension**

Reinforcing bar (rebar): ø8, ø10, ø12, ø14, ø16, ø20, ø22, ø24, ø25, ø28, ø32



- Minimum value of related rip area $f_{R,min}$ according to EN 1992-1-1:2004+AC:2010
- Rib height of the bar shall be in the range $0,05\phi \leq h \leq 0,07\phi$
(ϕ : Nominal diameter of the bar; h: Rip height of the bar)

Table A1: Materials

| Designation | Material |
|---|---|
| Rebar EN 1992-1-1:2004+AC:2010, Annex C | Bars and de-coiled rods class B or C f_{yk} and k according to NDP or NCL of EN 1992-1-1/NA:2013 $f_{uk} = f_{tk} = k \cdot f_{yk}$ |

Fix Master Injection system Fit-Ve 200 for rebar connection

Product description
Injection mortar / Static mixer / Rebar
Materials

Annex A 2

Specifications of intended use

Anchorage subject to:

- Static and quasi-static loads.

Base materials:

- Reinforced or unreinforced normal weight concrete according to EN 206-1:2000.
- Strength classes C12/15 to C50/60 according to EN 206-1:2000.
- Maximum chloride concrete of 0,40% (CL 0.40) related to the cement content according to EN 206-1:2000.
- Non-carbonated concrete.

Note: In case of a carbonated surface of the existing concrete structure the carbonated layer shall be removed in the area of the post-installed rebar connection with a diameter of $\phi + 60$ mm prior to the installation of the new rebar.

The depth of concrete to be removed shall correspond to at least the minimum concrete cover in accordance with EN 1992-1-1:2004+AC:2010.

The foregoing may be neglected if building components are new and not carbonated and if building components are in dry conditions.

Temperature Range:

- - 40°C to +80°C (max. short term temperature +80°C and max long term temperature +50°C).

Design:

- Anchorages are designed under the responsibility of an engineer experienced in anchorages and concrete work.
- Verifiable calculation notes and drawings are prepared taking account of the forces to be transmitted.
- Design according to EN 1992-1-1:2004+AC:2010 and Annex B 2.
- The actual position of the reinforcement in the existing structure shall be determined on the basis of the construction documentation and taken into account when designing.

Installation:

- Dry or wet concrete.
- It must not be installed in flooded holes.
- Hole drilling by hammer drill or compressed air drill mode.
- The installation of post-installed rebar shall be done only by suitable trained installer and under supervision on site; the conditions under which an installer may be considered as suitable trained and the conditions for supervision on site are up to the Member States in which the installation is done.
- Check the position of the existing rebars (if the position of existing rebars is not known, it shall be determined using a rebar detector suitable for this purpose as well as on the basis of the construction documentation and then marked on the building component for the overlap joint).


Fix Master Injection system Fit-Ve 200 for rebar connection

Intended use
Specifications

Annex B 1

Figure B1: General construction rules for post-installed rebars

- Only tension forces in the axis of the rebar may be transmitted
- The transfer of shear forces between new concrete and existing structure shall be designed additionally according to EN 1992-1-1:2004+AC:2010.
- The joints for concreting must be roughened to at least such an extent that aggregate protrude.



¹⁾ If the clear distance between lapped bars exceeds 4ϕ , then the lap length shall be increased by the difference between the clear bar distance and 4ϕ .

The following applies to Figure B1:

| | |
|----------|---|
| c | concrete cover of post-installed rebar |
| c_1 | concrete cover at end-face of existing rebar |
| $\min c$ | minimum concrete cover according to Table B1 and to EN 1992-1-1:2004+AC:2010, Section 4.4.1.2 |
| ϕ | diameter of post-installed rebar |
| ℓ_0 | lap length, according to EN 1992-1-1:2004+AC:2010, Section 8.7.3 |
| ℓ_v | effective embedment depth, $\geq \ell_0 + c_1$ |
| d_0 | nominal drill bit diameter, see Annex B 6 |


Fix Master Injection system Fit-Ve 200 for rebar connection

Intended use

General construction rules for post-installed rebars

Annex B 2

Table B1: Minimum concrete cover $\min c^1)$ of post-installed rebar depending of drilling method



| Drilling method | Rebar diameter | Without drilling aid | With drilling aid |
|------------------------------|----------------|---|---|
| Hammer drilling (HD) | < 25 mm | 30 mm + $0,06 \cdot \ell_v \geq 2 \phi$ | 30 mm + $0,02 \cdot \ell_v \geq 2 \phi$ |
| | ≥ 25 mm | 40 mm + $0,06 \cdot \ell_v \geq 2 \phi$ | 40 mm + $0,02 \cdot \ell_v \geq 2 \phi$ |
| Compressed air drilling (CD) | < 25 mm | 50 mm + $0,08 \cdot \ell_v$ | 50 mm + $0,02 \cdot \ell_v$ |
| | ≥ 25 mm | 60 mm + $0,08 \cdot \ell_v$ | 60 mm + $0,02 \cdot \ell_v$ |

¹⁾ see Annexes B2, Figures B1

Comments: The minimum concrete cover acc. EN 1992-1-1:2004+AC:2010 must be observed

Table B2: maximum embedment depth $\ell_{v,max}$

| Rebar | $\ell_{v,max}$ [mm] |
|--------|---------------------|
| ϕ | |
| 8 mm | 1000 |
| 10 mm | 1000 |
| 12 mm | 1200 |
| 14 mm | 1400 |
| 16 mm | 1600 |
| 20 mm | 2000 |
| 22 mm | 2000 |
| 24 mm | 2000 |
| 25 mm | 2000 |
| 28 mm | 1000 |
| 32 mm | 1000 |

Table B3: Base material temperature, gelling time and curing time

| Concrete temperature | Gelling- / working time ¹⁾ | Minimum curing time in dry concrete ⁵⁾ |
|----------------------|---------------------------------------|---|
| | t_{gel} | $t_{cure,dry}$ |
| -10°C bis -6°C | 90 min ²⁾ | 24 h |
| -5°C bis -1°C | 90 min ³⁾ | 14 h |
| 0°C bis +4°C | 45 min ³⁾ | 7 h |
| +5°C bis +9°C | 25 min ³⁾ | 2 h |
| +10°C bis +19°C | 15 min ³⁾ | 80 min |
| +20°C bis +24°C | 6 min ³⁾ | 45 min |
| +25°C bis +29°C | 4 min ³⁾ | 25 min |
| +30°C bis +40°C | 2,5 min ⁴⁾ | 15 min |

¹⁾ t_{gel} : maximum time from starting of mortar injection to completing of rebar setting.

²⁾ Cartridge temperature **must** be at minimum +15°C

³⁾ Cartridge temperature **must** be between +5°C and +25°C

⁴⁾ Cartridge temperature **must** be below +20°C

⁵⁾ In wet concrete the curing time $t_{cure,dry}$ has to be doubled up

Fix Master Injection system Fit-Ve 200 for rebar connection










Intended use

Minimum concrete cover

Maximum embedment depth / working time and curing times

Annex B 3

Table B4: Dispensing tools

| Cartridge type/size | Hand tool | | Pneumatic tool |
|---|---|--|--|
| Coaxial cartridges 150, 280, 300 up to 333 ml |  e.g. Type H 297 or H244C | |  e.g. Type TS 492 X |
| Coaxial cartridges 380 up to 420 ml |  e.g. Type CCM 380/10 |  e.g. Type H 285 or H244C |  e.g. Type TS 485 LX |
| Side-by-side cartridges 235, 345 ml |  e.g. Type CBM 330A |  e.g. Type H 260 |  e.g. Type TS 477 LX |
| Side-by-side cartridge 825 ml | - | - |  e.g. Type TS 498X |


All cartridges could also be extruded by a battery tool.

Fix Master Injection system Fit-Ve 200 for rebar connection

Intended Use
Dispensing tools

Annex B 4


A) Bore hole drilling



1. Drill a hole into the base material to the size and embedment depth required by the selected reinforcing bar with carbide hammer drill (HD) or a compressed air drill (CD). In case of aborted drill hole: the drill hole shall be filled with mortar.




Hammer drill (HD)




Compressed air drill (CD)

| Rebar - Ø | Drill - Ø |
|-----------|-----------|
| φ | [mm] |
| 8 mm | 12 |
| 10 mm | 14 |
| 12 mm | 16 |
| 14 mm | 18 |
| 16 mm | 20 |
| 20 mm | 25 |
| 22 mm | 28 |
| 24 mm | 32 |
| 25 mm | 32 |
| 28 mm | 35 |
| 32 mm | 40 |

B) Bore hole cleaning




or




- 2a. Starting from the bottom or back of the bore hole, blow the hole clean with compressed air (min. 6 bar) or a hand pump a minimum of four times. If the bore hole ground is not reached an extension shall be used.


For bore holes deeper than 240 mm, compressed air (min. 6 bar) **must** be used.



- 2b. Check brush diameter (Table B5) and attach the brush to a drilling machine or a battery screwdriver. Brush the hole with an appropriate sized wire brush > $d_{b,min}$ (Table B5) a minimum of four times. If the bore hole ground is not reached with the brush, a brush extension shall be used.



or



- 2c. Finally blow the hole clean again with compressed air (min. 6 bar) or a hand pump a minimum of four times. If the bore hole ground is not reached an extension shall be used.

For bore holes deeper than 240 mm, compressed air (min. 6 bar) **must** be used.

Fix Master Injection system Fit-Ve 200 for rebar connection


Intended Use

Installation instruction: Bore hole drilling and
Bore hole cleaning

Annex B 5

Table B5: Cleaning tools

Brush:



SDS Plus Adapter:



Brush extension:



| ϕ Rebar - ϕ | d_0 Drill bit - ϕ | d_b Brush - ϕ | $d_{b,min}$ min. Brush - ϕ |
|--------------------------|-----------------------------|-------------------------|---------------------------------------|
| (mm) | (mm) | (mm) | (mm) |
| 8 | 12 | 14 | 12,5 |
| 10 | 14 | 16 | 14,5 |
| 12 | 16 | 18 | 16,5 |
| 14 | 18 | 20 | 18,5 |
| 16 | 20 | 22 | 20,5 |
| 20 | 25 | 27 | 25,5 |
| 22 | 28 | 30 | 28,5 |
| 24 | 32 | 34 | 32,5 |
| 25 | 32 | 34 | 32,5 |
| 28 | 35 | 37 | 35,5 |
| 32 | 40 | 41,5 | 40,5 |




Hand pump (volume 750 ml)




**Rec. compressed air tool
hand slide valve (min 6 bar)**


C) Preparation of bar and cartridge



3. Attach the supplied static-mixing nozzle to the cartridge and load the cartridge into the correct dispensing tool.
For every working interruption longer than the recommended working time (Table B3) as well as for every new cartridges, a new static-mixer shall be used.



4. Prior to inserting the reinforcing bar into the filled bore hole, the position of the embedment depth shall be marked (e.g. with tape) on the reinforcing bar and insert bar in empty hole to verify hole and depth ℓ_v .
The reinforcing bar should be free of dirt, grease, oil or other foreign material.



5. Prior to dispensing into the anchor hole, squeeze out separately the mortar until it shows a consistent grey colour, but a minimum of three full strokes, and discard non-uniformly mixed adhesive components.


Fix Master Injection system Fit-Ve 200 for rebar connection

Intended Use


Installation instruction: Cleaning tools and
Preparation of bar and cartridge

Annex B 6

D) Filling the bore hole



6. Starting from the bottom or back of the cleaned anchor hole fill the hole up to approximately two-thirds with adhesive. Slowly withdraw the static mixing nozzle as the hole fills to avoid creating air pockets. For embedment larger than 190 mm an extension nozzle shall be used.




For overhead and horizontal installation and bore holes deeper than 240 mm a piston plug and the appropriate mixer extension must be used.

Observe the gel-/ working times given in Table B3.

Table B6: Piston plugs, max anchorage depth and mixer extension

| Bar size ϕ (mm) | Drill bit - Ø | | Piston plug No. | Cartridge: All sizes | | | | Cartridge: side-by-side (825 ml) | |
|-------------------------------|------------------|----|---------------------------|-------------------------|--------------------|--------------------|--------------------|-------------------------------------|--------------------|
| | | | | Hand or battery tool | | Pneumatic tool | | Pneumatic tool | |
| | HD | PD | | l _{v,max} | Mixer extension | l _{v,max} | Mixer extension | l _{v,max} | Mixer extension |
| (mm) | (mm) | | | (cm) | | (cm) | | (cm) | |
| 8 | 12 | - | - | 70 | VL 10/0,75 | 80 | VL 10/0,75 | 80 | VL 10/0,75 |
| 10 | 14 | - | #14 | | | 100 | | | |
| 12 | 16 | | #16 | | | 100 | | 120 | VL 16/1,8 |
| 14 | 18 | | #18 | | | | | 140 | |
| 16 | 20 | | #20 | | | | | 160 | |
| 20 | 25 | 26 | #25 | 50 | VL 10/0,75 | 70 | 200 | VL 16/1,8 | |
| 22 | 28 | | #28 | | | 50 | | | |
| 24 | 32 | | #32 | | | | | | |
| 25 | 32 | | #32 | | | | | | |
| 28 | 35 | | #35 | | | | 100 | | |
| 32 | 40 | | #40 | | | | | | |



Injection tool must be marked by mortar level mark l_m and anchorage depth l_v resp. $l_{e,ges}$ with tape or marker.

Quick estimation: $l_m = 1/3 \cdot l_v$

Continue injection until the mortar level mark l_m becomes visible.

Optimum mortar volume: $l_m = l_v$ resp. $l_{e,ges} \cdot \left(1,2 \cdot \frac{\phi^2}{d_0^2} - 0,2 \right)$ [mm]


Fix Master Injection system Fit-Ve 200 for rebar connection

Intended Use

Installation instruction: Filling the bore hole


Annex B 7

E) Inserting the rebar




7. Push the reinforcing bar into the anchor hole while turning slightly to ensure positive distribution of the adhesive until the embedment depth is reached.

The bar should be free of dirt, grease, oil or other foreign material.



8. Be sure that the bar is inserted in the bore hole until the embedment mark is at the concrete surface and that excess mortar is visible at the top of the hole. If these requirements are not maintained, the application has to be renewed. For overhead installation fix embedded part (e.g. wedges).



9. Observe gelling time t_{gel} . Attend that the gelling time can vary according to the base material temperature (see Table B3). It is not allowed to move the bar after gelling time t_{gel} has elapsed. Allow the adhesive to cure to the specified time prior to applying any load. Do not move or load the bar until it is fully cured (attend Table B3). After full curing time t_{cure} has elapsed, the add-on part can be installed.

Fix Master Injection system Fit-Ve 200 for rebar connection

Intended Use

Installation instruction: Inserting rebar

Annex B 8

Minimum anchorage length and minimum lap length

The minimum anchorage length $\ell_{b,min}$ and the minimum lap length $\ell_{0,min}$ according to EN 1992-1-1:2004+AC:2010 ($\ell_{b,min}$ acc. to Eq. 8.6 and Eq. 8.7 and $\ell_{0,min}$ acc. to Eq. 8.11) shall be multiply by a factor according to Table C1.

Table C1: Factor related to concrete class and drilling method

| Concrete class | Drilling method | Factor |
|------------------|---|--------|
| C12/15 to C50/60 | Hammer drilling and compressed air drilling | 1,0 |

Table C2: Design values of the ultimate bond resistance f_{bd} in N/mm² for all drilling methods for good conditions

according to EN 1992-1-1:2004+AC:2010 for good bond conditions
(for all other bond conditions multiply the values by 0.7)

| Rebar - Ø | Concrete class | | | | | | | | |
|--------------|----------------|--------|--------|--------|--------|--------|--------|--------|--------|
| ϕ | C12/15 | C16/20 | C20/25 | C25/30 | C30/37 | C35/45 | C40/50 | C45/55 | C50/60 |
| 8 to 25 mm | 1,6 | 2,0 | 2,3 | 2,7 | 3,0 | 3,4 | 3,7 | 4,0 | 4,3 |
| 28 bis 32 mm | 1,6 | 2,0 | 2,3 | 2,7 | 3,0 | 3,4 | 3,7 | 3,7 | 3,7 |

Fix Master Injection system Fit-Ve 200 for rebar connection

Performances

Minimum anchorage length and minimum lap length
Design values of ultimate bond resistance f_{bd}

Annex C 1